

**Kodak
Flexcel SRH
flexographic plates**

Kodak Flexcel SRH flexographic plates

FLEXOGRAPHIC PLATES

Technical specifications

Plate thickness	1.14mm / 0.045", 1.70mm / 0.067", 2.28mm / 0.090", 2.54mm / 0.100", 2.72mm / 0.107", 2.84mm / 0.112"	
Resolution	1% to 95% @ 150 lpi	
Isolated dot reproduction	100 - 130µm	
Fine line reproduction	70 - 100µm	
Plate hardness Shore A	SRH 1.14mm / 0.045": 73 SRH 1.70mm / 0.067": 64 SRH 2.28mm / 0.090": 62	SRH 2.54mm / 0.100": 60 SRH 2.72mm / 0.107": 60 SRH 2.84mm / 0.112": 59
Wash-out solution	Compatible with most wash-out solvents Recommended wash-out solvent temperature: 20°C - 35°C (68°F - 95°F)	
Ink compatibility	Aqueous, solvent-based, UV-cured and cationic inks	
Storage and handling	Unopened plate packs should be stored flat and away from excessive cold, heat and humidity. Use in a controlled environment of 10°C - 25°C (50°F - 77°F) and 40 - 55% RH.	

